

## Technical Data Sheet

# Greentherm<sup>®</sup> HVAC

CFC/HCFC Free Rigid Polyisocyanurate Insulation with a factory applied aluminium foil vapour barrier

### General Technical Properties

Property	Test Method	Unit	Typical Value
Nominal Dry Density	EN ISO 845	kg/m <sup>3</sup>	35 - 40
Thermal Conductivity	EN 12667 at +10°C		
	Initial	W/m·K	0.021
	Aged (25 weeks @ 70°C)	W/m·K	0.025
Colour			Green/Blue
Closed Cell Content	EN ISO 4590 Meth. 1	%	≥ 95
Operating Temperature Limits	Upper Limit	°C	+120
	Lower Limit	°C	-50
Compressive Strength	EN 826 at +23°C		
	Parallel	kPa	≥ 150
	Perpendicular	kPa	≥ 90
Tensile Strength	ASTM D 1623 – Spec. A at +23°C		
	Parallel	kPa	≥ 150
	Perpendicular	kPa	≥ 110
Linear Dimensional Stability	EN 1604		
	+93°C for 24 hours	%	≤ 1
	-30°C for 24 hours	%	≤ 1
Linear Expansion Coefficient	ASTM D 696	K <sup>-1</sup>	40-70 x 10 <sup>-6</sup>

### Technical Properties of the reinforced vapour barrier foil

Property	Test Method	Unit	Typical Value
Weight	DIN EN ISO 536	gr/m <sup>2</sup>	96
Thickness	EDANA	µm	471
Tensile Strength	DIN EN ISO 1924-2 (MD/CD)	N/15mm	>40 / >15
Elongation	DIN EN ISO 1924-2	%	< 7
Water vapour transmission	ASTM F 1249	gr/m <sup>2</sup> ·24hr	<0.1

### Fire Classifications

Property	Test Method	Typical Result
Reaction to fire	EN 13501-1	B <sub>1</sub> - s1, d0
Fire propagation	BS 476-6	Index of performance (I) not exceeding 12 and sub-index (i <sub>1</sub> ) not exceeding 6*
Flame spread	BS 476-7	Class 1*
Vertical burning characteristics	DIN 4102	B1**
Epiradiateur	NF P 92-501	M1

Green Products Industrial Insulation takes no responsibility for any application where products from Green Products Industrial Insulation are used without prior inquiry of Green Products Industrial Insulation. Green Products Industrial Insulation doesn't take any responsibility if the products are wrongly applied. The values mentioned on this sheet are typical and don't imply specification limits. Though the information reported in this data sheet is true and reflects Green products Industrial Insulation's best knowledge, we decline all responsibility for errors and omissions, damage or loss resulting here from it is always necessary to verify recommendations for use with regards to suitability and conformity with actual requirements, specifications and any applicable laws.